



MaxPox VE

Vinyl Ester Resin

INTRODUCTION

MaxPox VE is a corrosion resistant, epoxy vinyl ester resin for use in the manufacture of liner pipe using cured-in-place techniques. This resin is designed for ambient cure. The corrosion resistance of this resin is comparable to CORVE8100. Data on any specific testing or corrosion recommendations will be supplied upon request.



FEATURES

- Moderate Composite Exotherm
- Good Fiberglass Wet-Out
- Tested Under ASTM D2990 for Flexural Modulus Creep

BENEFITS

- Resistant to distortion during cure cycle
- High composites physical properties
- Retains structural integrity under load in severe conditions

LIQUID PROPERTIES	RESULTS
Viscosity, Brookfield Model LV, #3 Spindle @ 60 rpm, 77°F (25°C), cPs	400-600
100 grams of resin @ 77°F (25°C), initiated with 4.0% Perkadox CH-50 by weight *	
Gel Time, min:sec	20:00-25:00
Gel to Peak Exotherm, min:sec	5:00-10:00
Peak Exotherm	320-400°F (160-204°C)
Non-Volatile Content, %	54.0-60.0
Weight per Gallon, lbs.	8.60-9.00



TYPICAL PROPERTIES

Thickness	1/8 inch (3.2 mm) Casting		1/4 inch (6.4 mm) Laminate	
Construction	Not Applicable		CIPP Felt Laminate	
Flexural Strength, ASTM D790	19,000psi	131MPa	11,000psi	76MPa
Flexural Modulus, ASTM D790	4.7 x 10 ⁵ psi	3,241MPa	5.1 x 10 ⁵ psi	3,500MPa
Tensile Strength, ASTM D638	12,000psi	83MPa	6,800psi	47MPa
Tensile Modulus, ASTM D638	4.7 x 10 ⁵ psi	3,241MPa	5.3 x 10 ⁵ psi	3,700MPa
Tensile Elongation, ASTM D638	4.5%	4.5%	2.0%	2.0%
Barcol Hardness, 934-1 gauge, ASTM D2583	36	36	N/A	N/A
Heat Distortion Temperature, ASTM D648	210°F	98°C	197°F	92°C

* Gel time and reactivity will vary due to the type and concentration of Free Radical Initiator (catalyst), shop temperature, humidity, and type of fillers used. In order to meet your individual needs consult our technical sales representative for assistance.

All specifications and properties specified above are approximate. Specifications and properties of material delivered may vary slightly from those given above. Maxliner™ makes no representations of fact regarding the material except those specified above. No person has any authority to bind Maxliner to any representation except those specified above. Final determination of the suitability of the material for the use contemplated is the sole responsibility of the Buyer. Our technical sales representatives will assist in developing procedures to fit individual requirements, but all advice is accepted at your risk and should be checked for suitability to your particular processes. These test data and properties are based on results obtained for a specific material under the specified test conditions. They are not to be used as specifications and are not warranted as performance attributes for any product or system. Specifications and properties of standard production material may vary slightly from those in this report. Maxliner makes no warranties regarding any material and/or samples described in this report unless that representation is provided to your company in writing by a Technical Director of Maxliner or one of his or her managers.